



## BOSS® PU FOAM UNIVERSAL

### TECHNICAL DATA

Basis	Polyurethane
Consistency	Stable foam, thixotropic
Curing System	Moisture curing
Skin Formation* (FEICATM 1014)	8 min
Cutting Time* (FEICA TM 1005)	30 min
Free foamed density (FEICA TM 1019)	Ca. 29 kg/m <sup>3</sup>
Sound insulation (EN ISO 717-1)	58 dB
Thermal conductivity (FEICA TM 1020)	29.7 mW/m.K
Box Yield (FEICA TM 1003)	750 ml yields ca. 29 l of foam
Joint Yield (FEICA TM 1002)	750 ml yields ca. 20 m of foam
Shrinkage after curing (FEICA TM 1004)	< 2 %
Expansion after curing (FEICA TM 1004)	< 2 %
Expansion during curing (FEICA TM 1010)	Ca. 141 %
Percentage closed cells (ISO4590)	Ca. 7 %
Water absorption (EN1609)	Ca. 0.23 kg/m <sup>2</sup>
Reaction to fire classification (EN 13501-1)	No fire classification (F)
Compressive strength (FEICA TM 1011)	Ca. 21 kPa
Shear strength (FEICA TM 1012)	Ca. 52 kPa
Tensile Strength (FEICA TM 1018)	Ca. 77 kPa
Elongation at Fmax (FEICA TM 1018)	Ca. 14.7 %
Temperature resistance**	-40 °C till +90 °C (cured)

\* These values may vary depending on environmental factors such as temperature, moisture, and type of substrates.

\*\* This information relates to fully cured product.

### Description

BOSS® PU FOAM UNIVERSAL is a one-component, self-expanding, ready-to-use, PU-foam, which contains HCFC-and CFC-free propellants, which are not harmful for the ozone layer.

- High thermal and acoustic insulation value
- Very good bonding properties
- Not UV-resistant
- Freon free (not harmful to ozone layer and greenhouse effect)

### Benefits

- Excellent stability (no shrinkage or post-expansion)
- High filling capacity
- Good adhesion on all surfaces (except PE, PP and PTFE)

### Applications

- Filling of cavities
- Sealing of all openings in roof constructions
- Apply of an acoustic baffle



# BOSS® PU FOAM UNIVERSAL

- Improving thermal isolation in cooling systems
- All foam applications in static joints

## Packaging

Colour: Champagne  
Packaging: 750 ml aerosol (net)

## Shelf life

18 months if unopened and stored in dry and cool conditions (Between 5 and 25 °C), Upright storage is recommended.

## Application method

Shake the aerosol can for at least 20 seconds. Put the adapter on the valve. Moisten surfaces with a water sprayer prior to application. For non-conventional substrates, a preliminary adhesion test is recommended. Remove pressure from the applicator to stop. Fill holes and cavities for 1/3, as the foam will expand. Repeat shaking regularly during application. If you have to work in layers, repeat moistening after each layer. Fresh foam can be removed using Gun & Foam cleaner or acetone. Cured foam can only be removed mechanically or with PU Remover.

Can temperature: +5 °C - 30 °C  
Ambient temperature: +5 °C - 30 °C.  
Surface temperature: +5 °C - 35 °C

## Health and Safety Recommendations

Take the usual labour hygiene into account. Always wear gloves and goggles. Remove cured foam mechanically. Never burn away. Consult label and material safety data sheet for more information. When vaporizing (for example with a compressor), additional security measures will be required. Use only in well-ventilated areas.

## Remarks

Moisten surfaces with a water sprayer prior to application. If you have to work in layers, repeat moistening after each layer. For uncommon surfaces, we recommend an adhesion test.

## Environmental clauses

Leed regulation:  
BOSS® PU FOAM UNIVERSAL conforms to the requirements of LEED. Low -Emitting Materials: Adhesives and Sealants. SCAQMD rule 1168. Complies with USGBC LEED 2009 Credit 4.1: Low- Emitting Materials – Adhesives & Sealants concerning the VOC-content.

## Users please read

The information and data contained herein is believed to be accurate and reliable; however, it is the user's responsibility to determine suitability of use. Since the supplier cannot know all the uses, or the conditions of use to which these products may be exposed, no warranties concerning the fitness or suitability for a particular use or purpose are made. It is the user's responsibility to thoroughly test any proposed use of our products and independently conclude satisfactory performance in the application. Likewise, if the application, product specifications or manner in which our products are used requires government approval or clearance, it is the sole responsibility of the user to obtain sure authorization. The supplier warrants only that its products will meet its specifications. There is no warranty of merchantability or fitness for use, nor any other express or implied warranty. The users exclusive remedy and the suppliers sole liability is limited to refund of the purchase price or replacement of any product shown to be otherwise than as warranted. The supplier will not be liable for incidental or consequential damages of any kind. Suggestions of uses should not be taken as inducements to infringe any patents.

**Disclaimer:** This technical data sheet replaces all previous versions. The directives contained within this documentation are the result of our experiments and experience, and have been submitted in good faith. Because of the diversity of the materials and substrates, in addition to the great number of possible applications that go beyond our control, we cannot accept any responsibility for the results obtained. Further, since the design, quality of the substrate, and processing conditions are beyond our control, no liability under this publication will be accepted. In every case, it's therefore recommended to carry out preliminary experiments. BOSS reserves the right to modify its products, without prior notice.

### Accumetric Silicones Pvt Ltd

No. 16/1, Corporation Road, Seevaram, Perungudi, Chennai - 600 096, Tamil Nadu, India.  
Customer Support: +91 44 4026 0345 - 60  
indiasales@bossproducts.com  
www.bossproducts.in