

BOSS® TVB ACRYLIC AEROSOL LACQUER PAINT

TECHNICAL DATA

Type	100% Acrylic Solvent-based
Colour	Refer to BOSS® TVB acrylic aerosol lacquer shade card
Gloss 60° (%)	80-90% (Gloss paints)
Gloss 60° (%)	0-5% (Flat paints)
Adhesion (%) (cross cut)	90-100
Flexibility (Ø 3 mms, Mandrel)	Passed
Wet film thickness (µ)	~50µ / coat.
Dry film thickness (µ)	~25µ / coat.
Drying time	
Touch dry (min)	5-10
Hard dry (min)	25-30

Description

BOSS® TVB Acrylic Aerosol Lacquer is formulated on 100% Acrylic Resin to give the best available aerosol quality product. It is quick drying, high gloss and has excellent adhesion on metals, steels, wood and plastic surfaces. It is lead-free and mercury-free and can be used for several applications such as furniture, toys, automotive, bicycles, motorcycles etc.

Direction for use

- Surface should be clean. Remove rust, dirt, moisture, grease, wax etc.
- Shake well for about 1-2 minutes before using and shake periodically during spray.
- Spray from a distance of about 1 foot.
- For better results, apply several thin coatings with intervals of 10 minutes in between.
- After spraying, turn can upside down and press spray head to clean the spray nozzle.

CAUTION :

- Do not spray near fire or open flame
- Do not store above 40°C
- Do not expose can container to heat or direct sunlight
- Use only with adequate ventilation
- Do not throw away or incinerate can
- Keep away from children

BOSS® TVB ACRYLIC AEROSOL LACQUER PAINT

Users Please Read

The information and data contained herein is believed to be accurate and reliable; however, it is the user's responsibility to determine suitability of use. Since the supplier cannot know all the uses, or the conditions of use to which these products may be exposed, no warranties concerning the fitness or suitability for a particular use or purpose are made. It is the user's responsibility to thoroughly test any proposed use of our products and independently conclude satisfactory performance in the application. Likewise, if the application, product specifications or manner in which our products are used requires government approval or clearance, it is the sole responsibility of the user to obtain sure authorization. The supplier only warrants that its products will meet its specifications. There is no warranty of merchantability or fitness for use, nor any other express or implied warranty. The users exclusive remedy and the suppliers sole liability is limited to refund of the purchase price or replacement of any product shown to be otherwise than as warranted. The supplier will not be liable for incidental or consequential damages of any kind. Suggestions of uses should not be taken as inducements to infringe any patents.

Disclaimer: This technical data sheet replaces all previous versions. The directives contained within this documentation are the result of our experiments and experience, and have been submitted in good faith. Because of the diversity of the materials and substrates, in addition to the great number of possible applications that go beyond our control, we cannot accept any responsibility for the results obtained. Further, since the design, quality of the substrate, and processing conditions are beyond our control, no liability under this publication will be accepted. In every case, it's therefore recommended to carry out preliminary experiments. BOSS reserves the right to modify its products, without prior notice.

Accumetric Silicones Pvt Ltd

No. 16/1, Corporation Road, Seevaram, Perungudi,
Chennai - 600 096, Tamil Nadu, India.
Customer Support: +91 44 4026 0345 - 60
indiasales@bossproducts.com
www.bossproducts.in